

Fig. 1

Staple fiber to which ester from PEG and fatty acid is applied is provided as raw material, and the staple fiber is opened and carded to obtain a web.

-10

Binding to obtain non-woven fabric -11

5

Heat treatment -12

Electric charging -13

10 Electret non-woven fabric -14

10/062,568/Sheet 1 of 1
Atty. Dkt.: 330-244
Inventor: TAI, et al.
SN 10/062,568/Sheet 1 of 1
Atty. Dkt.: 330-244